

[www.chtisma.com.cy](http://www.chtisma.com.cy)

Alpeon 8, Industrial Area Agiou Sila, 4193, Ipsonas – Limassol, CYPRUS  
Tel: 25395280 fax: 25394671. E-mail: [chtisma@cytanet.com.cy](mailto:chtisma@cytanet.com.cy)



|                                      |   |
|--------------------------------------|---|
| <b>Thickness</b>                     | <b>3mm</b>                                |
| <b>Weight</b>                        | <b>230g/m<sup>2</sup></b>                 |
| <b>Roll Dimension</b>                | <b>1.20 x 50m = 60m<sup>2</sup></b>       |
| <b>Bubble Diameter</b>               | <b>10mm</b>                               |
| <b>Reflectivity</b>                  | <b>97% in Radiant Energy (ASTM C1371)</b> |
| <b>Color</b>                         | <b>Silver</b>                             |
| <b>Water Vapor</b>                   | <b>0.0018 (ASTM E96)</b>                  |
| <b>Corrosion</b>                     | <b>0 (ASTM D3310)</b>                     |
| <b>Thermal Resistance R-Value</b>    | <b>1.428m<sup>2</sup> K/W (ASTM C236)</b> |
| <b>Thermal Transmittance U-Value</b> | <b>0.700 W/km<sup>2</sup> (ASTM C326)</b> |
| <b>Thermal Conductivity</b>          | <b>λ 0.0021 W/Mk (TYPOLOGY)</b>           |

|                                      |   |
|--------------------------------------|---|
| <b>Thickness</b>                     | <b>5mm</b>                                |
| <b>Weight</b>                        | <b>280g/m<sup>2</sup></b>                 |
| <b>Roll Dimension</b>                | <b>1.20 x 40m = 48m<sup>2</sup></b>       |
| <b>Bubble Diameter</b>               | <b>10mm</b>                               |
| <b>Reflectivity</b>                  | <b>97% in Radiant Energy (ASTM C1371)</b> |
| <b>Color</b>                         | <b>Silver</b>                             |
| <b>Water Vapor</b>                   | <b>0.0018 (ASTM E96)</b>                  |
| <b>Corrosion</b>                     | <b>0 (ASTM D3310)</b>                     |
| <b>Thermal Resistance R-Value</b>    | <b>2.083m<sup>2</sup> K/W (ASTM C236)</b> |
| <b>Thermal Transmittance U-Value</b> | <b>0.480 W/km<sup>2</sup> (ASTM C326)</b> |
| <b>Thermal Conductivity</b>          | <b>λ 0.0024 W/Mk (TYPOLOGY)</b>           |

|                                      |   |
|--------------------------------------|---|
| <b>Thickness</b>                     | <b>7mm</b>                                |
| <b>Weight</b>                        | <b>340g/m<sup>2</sup></b>                 |
| <b>Roll Dimension</b>                | <b>1.20 x 40m = 48m<sup>2</sup></b>       |
| <b>Bubble Diameter</b>               | <b>10mm</b>                               |
| <b>Reflectivity</b>                  | <b>97% in Radiant Energy (ASTM C1371)</b> |
| <b>Color</b>                         | <b>Silver</b>                             |
| <b>Water Vapor</b>                   | <b>0.0018 (ASTM E96)</b>                  |
| <b>Corrosion</b>                     | <b>0 (ASTM D3310)</b>                     |
| <b>Thermal Resistance R-Value</b>    | <b>2.597m<sup>2</sup> K/W (ASTM C236)</b> |
| <b>Thermal Transmittance U-Value</b> | <b>0.385 W/km<sup>2</sup> (ASTM C326)</b> |
| <b>Thermal Conductivity</b>          | <b>λ 0.0027 W/Mk (TYPOLOGY)</b>           |