

VODICOLOR EXTRA

VODICHEM

ELASTIC COLOURED WATERPROOFING MEMBRANE

PRODUCT DESCRIPTION

VODICOLOR EXTRA is a coloured waterproofing protective membrane, based on synthetic resins in water dispersion and its dried film is characterized by high elasticity and by high waterproof power.

PRIMARY USES

Thanks to its formulation **VODICOLOR EXTRA** has got very good covering power and can be applied on every kind of bituminous covering on cement supports, plasters, on asbestos cement large slabs.

It is used as an anchoring protective on the old slate membranes with the aim of prevent the crumbling of slate flakes and to restore the uniform colouration. The high quality of the elastomeric resins, additives and pigments contained in the product grant an excellent water impermeability and a good vapour permeability. The dried film is elastic and flexible in order to compensate possible "movements" of the support where is applied.

VODICOLOR EXTRA offers excellent resistance to acid rains, to aggressive atmosphere and to the sun's ultraviolet rays.

The resistance to foot traffic of the dried film is good but it may be improved by interposing between the coats of **VODICOLOR EXTRA** a framework of now woven polyester (**VODITES**) easily soaking.

VODICOLOR EXTRA is used for the colorating sport floors made with conglomerates of cement or bituminous well-drained.

INSTRUCTIONS FOR USE

Clean carefully the support removing dust and crumbly parts. Possible big cracks should be repaired by means of grouts or adhesive water cement mixed with **VODILATEX**. In this case it is better to wait until the work of restoration is dried. It is always better to apply a first bed coat made by watering **VODICOLOR EXTRA** down by 10%. When the drying-process has taken place (2 hours at 20° C) **VODICOLOR EXTRA** can be applied again without diluting it. The application may be carried out by means of a brush, a roller or a trowel or with an airless pump. The consumption varies from Kg. 0,200 to a 250 for square metre for the first coat.

For the last coat it can be used from Kg. 0,300 to 0,500 for square metre.

LIQUID ELASTO-BITUMINOUS AND
SYNTHETIC WATERPROOFING PRODUCTS.
PROTECTIVE AND CHEMICAL PRODUCTS
FOR THE BUILDING INDUSTRY.