

TECHNICAL FEATURES

VODICOLOR EXTRA

Colours:	white, brick red, green, grey, brown, light blu.	
Specific gravity:	Kg. 1,350 /dm. ³	
Dry residue:	68%	
Elongation and break:	600%	
Resistance to traction:	longitudinal sense	16 by N/cm ²
	transversal sense	18 by N/cm ²
Cold flexibility:	-10°C	
Impermeability:	total	
Dilution:	clean water	
Packing:	plastic pails of Kg. 5 - 10 - 20	

PRECAUTIONS

Remember not to apply VODICOLOR EXTRA when weather is bad, if rain is expected within the next few hours or at temperatures below +5° C. These conditions should be ensured for at least 24 hours after applications.

For the waterproof of little cement masses or preexistent floors, it is better to use **VODITES** (elastic non woven polyester of 40 g.) interposed between the two coats of **VODICOLOR EXTRA**.

Provide for suitable slopes of the concretes in order to avoid prolonged water stagnation over the VODICOLOR EXTRA film.

Always foresee an element of connection between the horizontal plane and the vertical one. **VODICOLOR EXTRA** can not be applied on surfaces which contain hydraulic lime or chalk.

Keep the steel cans in the original packing in closed spots.

The product is sensitive to cold.

VODICHEM

ITALIA srl

Via A. Volta, 70 (Z.R.) C.P. 144
Tel. 0039/080/3628233-3614462 Fax 0039/080/3612944
70037 RUVO DI PUGLIA (Ba) ITALY