

TECHNICAL DATA SHEET

Date of issue: 2020

SOVADUR 908

DESCRIPTION

SOVADUR is an acrylic water based primer containing fine quartz aggregates. Suitable for adhesion improvement of smooth, non absorbent surfaces and absorbent or slightly unsound surfaces.



TECHNICAL CHARACTERISTICS	
Density	: 1,42 - 1,45(EAOTENISO 2811 20°C)
Viscosity	: 16000 -22000 mPas(ASTMD2196-86 25°C)
pH	: 8.6-8.9(ASTM E70)
Thinning	: 5-10% with water
Coverage	: 10m ² /lt per layer
Drying time	: Touch dry after 1 hour and recoatable after 2-3 hours
Colors	: Unlimited number of shades through tinting system of TETRALUX.
Packaging	: 3lt, 10lt
VOC (VolatileOrganic	: EU limit value for this product Category A: "g", Type:WB, primers:
Compounds)	30g/l (2010). This product contains max 29g/l VOC
Painting tools	: Brush, roller
	Remove as much paint as possible from the equipment in the container
	and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Storeattemperatures from 5°C to 40°C. Close the container after every
	use.



TECHNICAL DATA SHEET

Date of issue: 2020

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances

HEALTH, SAFETYAND ENVIRONMENTAL INFORMATION

Keep out of reach of children ● If medical advice is needed, have product container or label at hand ● Do not get in eyes, on skin, or on clothing. ● Call a POISON CENTER or doctor/physician if you feel unwell ● Dispose of contents/container in accordance with applicable regional, national and local laws and regulations Contains: 2-methylisothiazol-3(2H)-one, reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1). May produce an allergic reaction Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.

Tel. POISON CENTER: 210 7793777