



TECHNICAL DATA SHEET

Date of issue: 2020

SOVALUX FINE 553-556

DESCRIPTION

Acrylic, elastomeric, water repellent wall plaster ready to use. It has excellent adhesion to all masonry types like concrete, plaster, cement, etc. Does not need to be over-coated by paint. Due to its elasticity, it is ideal as topcoat to the constructions for subsequent insulation of buildings.



TECHNICAL CHARACTERISTICS

Density	: 1,74 - 1,83 (ΕΛΟΤ EN ISO 2811 20°C)
Viscosity	: 45.000 - 55.000 mPas (ASTM D2196-86 25°C)
pH	: 8.6 - 8.9 (ASTM E70)
Thermal conductivity	: $\lambda=0,7W(mk)$
Thinning	: Without dilution
Coverage	: 1,5-2,8 kg/m ² depend on the granule size ,the desired decorative finish and the use

Product	Granule size	Thickness of layer	Consumption
SOVALUX FINE	0.3mm	0.3mm	1.2-1.5kg/m ²
SOVALUX FINE	1mm	1mm	1.5-1.8kg/m ²
SOVALUX FINE	1.5mm	1.5mm	2-2.3kg/m ²
SOVALUX FINE	2mm	2mm	2.5-2.8kg/m ²

Drying time	: Touch dry after 1 hour and recoat able after 2-3hours
Colors	: Unlimited number of shades through tinting system of TETRALUX.
Packaging	: 18kg, 25kg
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "i", Type:WB, One pack performance coatings: 140g/l (2010). This product contains <140g/l VOC.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



TECHNICAL DATA SHEET

Date of issue: 2020

Painting tools	: Spatula or appropriate machine Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.

APPLICATION

Stir well before use

The substrate must be clean, dry and free of foreign matter and substances. First apply a layer with the special primer SOVADUR or TETRADUR primer (waterproof primers with high penetration and strong adhesion). After the primer dries, stir the material well and apply using a stainless polished spatula or an appropriate machine. While the Sovalux Fine layer is fresh (about 15-20 minutes later), the surface is 'pressed' or 'scrubbed' using a plastic spatula.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Keep out of reach of children • If medical advice is needed, have product container or label at hand • Do not get in eyes, on skin, or on clothing. • Call a POISON CENTER or doctor/physician if you feel unwell • Dispose of contents/container in accordance with applicable regional, national and local laws and regulations

Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist

Contains: 2-methylisothiazol-3(2H)-one, reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1). May produce an allergic reaction.

Tel. POISON CENTER: 210 7793777

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr