



TECHNICAL DATA SHEET

Date of issue: 2022

SOLVENT BASED VELATURA TETRAPRIMER

DESCRIPTION

A high quality, alkyd undercoat suitable for interior and exterior wooden and plastered surfaces. It has great hiding power, it can be sanded and applied easily, not affecting the enamel's finishing surface.



TECHNICAL CHARACTERISTICS

| | |
|---|---|
| Density | : 1,49 – 1,52 (EAOT EN ISO 2811 20°C) |
| Viscosity | : 80-85 KU (25°C) |
| Thinning | : 5% with solvent No803 |
| Coverage | : 13 - 14 m ² /lt per layer |
| Drying time | : Touch dry after 3 hours and recoat able after 16 hours |
| Colors | : Unlimited number of shades through tinting system of TETRALUX. |
| Packaging | : 750ml, 2.5lt, 5lt, 20lt |
| VOC (Volatile Organic Compounds) | : EU limit value for this product Category A: "g", Type:SB, Primers: 350g/l (2010). This product contains max 349g/l VOC. |
| Painting tools | : Brush, roller, pistol Remove as much paint as possible from the equipment in the container and clean it immediately with solvent No806 or No803 and then wash with hot water and soap. |
| Conditions of application | : Do not apply at temperatures below 10°C and above 35°C. |
| Storage | : Store at temperatures from 5°C to 40°C. Close the container after every use. |

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



TECHNICAL DATA SHEET

Date of issue: 2022

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.